

TEST REPORT

Number : SHAT06681616
报告号:

Applicant : WUJIANG TUTAIKE TEXTILES & FINISHING
申请公司: 吴江市涂泰克纺织后整理有限公司
NO. 1599, SOUTH THIRD RING, SHENGZE
TOWN, WUJIANG CITY, JIANGSU PROVINCE
江苏省苏州市吴江区盛泽镇南三环 1599 号
Attn : ZHANG YANWEN
联系人: 张燕文

Date : Oct 29, 2020
日期: 2020 年 10 月 29 日

Sample Description :

样品描述 样品数量:

Six Pieces Of Sample Said To Be PP+MBE Non-Woven Surgical Gown In White.

客户认定为 6 件 PP+MBE 无纺布手术衣, 颜色为白色.

Applicant's Provided Care Instruction/Label : -

申请人所提供之水洗标签:-

Date Received/Date Test Started : OCT 19-2020

接件日期/测试开始日期 10-19-2020

Standard : -

标准

Order No. :

定单号

Style No. : TTK-C09 White

款号

Buyer's Name : TTK-C09 White

买主

Manufacturer's Name : Wujiang Tutaike Textiles & Finishing Co., Ltd

生产商名字

Document Accordance : 吴江市涂泰克纺织后整理有限公司

判定依据 : -

Test Type : Commission Test (Submitted Test)

检验类别

Remark : 委托检验(送样检验)

备注 : The English Version Of This Test Report Is Standard One, The Chinese

Version Is Only For Reference

此报告以英文为主, 中文仅供参考

Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai



Jennifer Ren
General Manager

TEST REPORT

Number : SHAT06681616
报告号:



Prepared And Checked By:
For Intertek Testing Services Ltd., Shanghai

Jennifer Ren
General Manager

Page 2 Of 8

Intertek Testing Services Ltd., Shanghai

2/F, Building No.4, Shanghai Comalong Technology Service Park,
889 Yishan Road, Shanghai 200233, China
上海天祥质量技术服务有限公司

中国上海宜山路 889 号上海齐来科技服务园区 4 号楼 2 楼 邮编:200233

Tel: +86 21 5339 5999 Fax: +86 21 5426 2030 E-mail: textile.shanghai@intertek.com Website: Intertek.com

Attention is drawn to the terms and conditions printed overleaf

TEST REPORT

Number : SHAT06681616
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容（以下测试依据申请人要求进行）

1 Water Resistance As Received -Impact Penetration Test Method (AATCC 42-2017):

防漏水性（初始状态样品）- 冲击渗透测试方法（AATCC 42-2017）:

(Test On Body Fabric)

(测试在大身面料上)

(Grams Of Water Absorbed)

(吸收的水量, 克)

Specimen 1	0.1 g
试样 1	0.1 克
Specimen 2	0.1 g
试样 2	0.1 克
Specimen 3	0.1 g
试样 3	0.1 克
Average	0.1 g
平均值	0.1 克

(Test On Seam At Shoulder)

(测试在肩膀处接缝)

(Grams Of Water Absorbed)

(吸收的水量, 克)

Specimen 1	0.1 g
试样 1	0.1 克
Specimen 2	0.1 g
试样 2	0.1 克
Specimen 3	0.1 g
试样 3	0.1 克
Average	0.1 g
平均值	0.1 克

TEST REPORT

Number : SHAT06681616
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

- 2 Hydrostatic Pressure Test As Received (AATCC 127-2014, Method A, Option 2, Hydrostatic Head Tester, Pressure Gradient At 60 mbar/min Water Pressure):
静水压试验(初始状态样品) (AATCC 127-2014, Method A, Option 2, Hydrostatic Head Tester, 水压上升速率 60mbar/min):

(Test On Body Fabric)

(测试在大身面料上)

4215 mm*

4215 毫米*

(Test On Seam At Shoulder)

(测试在肩膀处接缝)

6210 mm*

6210 毫米*

Remark: * = Film Burst Was Found

* = 面料破裂

TEST REPORT

Number : SHAT06681616
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

3 Resistance against penetration of Phi-X174 bacteriophage

抗血液携带病原体穿透性

Test Method: ASTM F1671/F1671M-2013

测试方法: ASTM F1671/F1671M-2013

Test principle:

测试原理:

A specimen is subjected to a nutrient broth containing a virus for a specified time and pressure sequence. Visual detection of penetration is supplemented with an assay procedure that will detect viable viruses which penetrate the material even when liquid penetration is not visible. Any evidence of viral penetration for a test specimen constitutes failure.

按规定的压力和时间程序, 试样要承受带有病菌营养肉汤的穿透。当没有出现材料被液体穿透情况下, 目视检测穿透作为发现病菌一个补充化验程序, 病菌穿透试样的任何现象记录为不符合。

Test equipment:

测试设备:

Hydrostatic tester

静水压测试仪

Incubator

恒温培养箱

Electronic balance

电子天平

Autoclave

压力蒸汽灭菌锅

Retaining screen

支撑网

TEST REPORT

Number : SHAT06681616
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

3 Resistance against penetration of Phi-X174 bacteriophage (CONT'D)

抗血液携带病原体穿透性(续)

The environmental conditions of the laboratory and test condition:

实验室环境条件和测试条件:

Pretreatment: Condition the test specimens at 24.5°C air at 56.0% RH for more than 24 h

预处理条件: 温度 24.5°C、相对湿度 56.0%环境中预处理超过 24h

Culture Medium: top agar and bottom agar

培养基名称: 上层琼脂、下层琼脂

Dimensions of the test specimens: 75mm×75mm

试样尺寸: 75mm×75mm

Culture temperature: 36°C, Culture time: 6~18 h

样品培养温度: 36°C, 样品培养时间: 6~18 h

Use retaining screen

有支撑网

Test virus: phi-X174 bacteriophage

测试病毒: 噬菌体 phi-X174

Assay 2.1×10^8 PFU/mL

试验滴度: 2.1×10^8 PFU/mL

TEST REPORT

Number : SHAT06681616
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

3 Resistance against penetration of Phi-X174 bacteriophage (CONT'D)

抗血液携带病原体穿透性(续)

Results:

结果:

Sample 样品	Test results 测试结果				Pass/Fail 测试通过/ 测试失败
	Step 1 步骤 1 (0kPa, 5min)	Step 2 步骤 2 (13.8kPa, 1min)	Step 3 步骤 3 (0kPa, 54min)	Assay titer 滴度 (PFU/ml)	
Control (+) 阳性对照	Seen 可见穿透	Seen 可见穿透	Seen 可见穿透	Seen 可见穿透	Acceptable 试验有效
Control (-) 阴性对照	None seen 不可见穿透	None seen 不可见穿透	None seen 不可见穿透	<1 <1	Acceptable 试验有效
Material 面料	None seen 不可见穿透	None seen 不可见穿透	None seen 不可见穿透	<1 <1	Pass 测试通过
Sleeve seam 袖缝	None seen 不可见穿透	None seen 不可见穿透	None seen 不可见穿透	<1 <1	Pass 测试通过

TEST REPORT

Number : SHAT06681616
报告号:

Tests Conducted (As Requested By The Applicant)
测试内容 (以下测试依据申请人要求进行)

3 Resistance against penetration of Phi-X174 bacteriophage (CONT'D)
抗血液携带病原体穿透性(续)

Requirement 技术要求	---
Judgement standard 判定标准	---
Conclusion 单项结论	---

Remark: Test Item is subcontracted to the organization accredited by CNAS with code of L10314 and CMA with code 170000113982.

备注: 测试项目为已获得资质认定和符合 ISO/IEC 17025 要求的分包项目, 分包方 CNAS 编号 L10314 和 CMA 编号 170000113982。

End of Report

Remark: The testing data and result issued by this report is just for reference only, not be used as the evidence to the society in the territory of the People's Republic of China.

备注: 本报告所出具的检测数据及结果仅供参考, 在中华人民共和国境内对社会不具有证明作用。

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.

本报告仅基于申请人的指示及/或申请人提供的信息和材料而作出, 不应视为采取任何行动的建议。关于本报告, Intertek 不对客户以外的任何人负有谨慎责任或其他责任, Intertek 对客户也只在向其申请人提供服务的条件条款有明确规定的范围承担责任。Intertek 不就本报告作出除前述条件条款范围之外的任何明示或隐含形式的担保或陈述。Intertek 致力于在勤勉细致的基础上进行审核, 不对因本报告引起的或与本报告有关的任何损失承担任何责任, 包括合同、侵权、法规或其它责任, 除非诉讼结果显示为因 Intertek 严重疏忽或故意的不当行为而造成。

未经本实验室书面批准, 不得复制本检测报告 (全文复制除外)。