

TEST REPORT

Number : SHAT06731207  
报告号:

Applicant : WUJIANG TUTAIKE TEXTILES & FINISHING  
申请公司: 吴江市涂泰克纺织后整理有限公司  
NO. 1599, SOUTH THIRD RING, SHENGZE  
TOWN, WUJIANG CITY, JIANGSU PROVINCE  
江苏省苏州市吴江区盛泽镇南三环 1599 号  
Attn : ZHANG YANWEN  
联系人: 张燕文

Date : Dec 03, 2020  
日期: 2020 年 12 月 03 日

**Sample Description As Declared :**

样品描述:

No. Of Sample : Eleven (11)  
样品数量  
Fibre Content : Non-Woven PP + PE  
成分 无纺布 PP+PE  
Sample Name : Hazmat Protective Suit  
样品名称 医用一次性防护服  
Finishing : -  
处理  
End Uses : -  
最终用途  
Colour : White  
颜色 白色  
Style No. : TTK-A01  
款号 TTK-A01  
Order No./PO No. : -  
订单号  
Buyer's Name : -  
买家名称  
Manufacturer's Name : Wujiang Tutaike Textiles & Finishing Co., Ltd  
供应商名称 吴江市涂泰克纺织后整理有限公司  
Ref. : -  
参考

Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai



Jennifer Ren  
General Manager

TEST REPORT

Number : SHAT06731207  
报告号:

Applicant's Provided Care Instruction/Label : -  
申请人所提供之水洗标签: -

Date Sample Received : Nov 26, 2020  
收件日期 11-26-2020  
Date Testing Started : Nov 26, 2020  
测试开始日期 11-26-2020  
Standard : ANSI/AAMI PB 70:2012 Liquid Barrier Performance And Classification Of Protective  
标准 Apparel And Drapes Intended For Use In Health care Facilities-Level 3  
ANSI/AAMI PB 70:2012 用于卫生健康设施的防护服和防护单的液体阻隔性能及分类-等级  
3  
Remark : The English Version Of This Test Report Is Standard One, The Chinese Version  
备注 Is Only For Reference  
此报告以英文为主, 中文仅供参考

Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai



Jennifer Ren  
General Manager

TEST REPORT

Number : SHAT06731207  
报告号:



Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai

Jennifer Ren  
General Manager

**Intertek Testing Services Ltd., Shanghai**

2/F, Building No.4, Shanghai Comalong Technology Service Park,  
889 Yishan Road, Shanghai 200233, China  
上海天祥质量技术服务有限公司

中国上海宜山路 889 号上海齐来科技服务园区 4 号楼 2 楼 邮编:200233

Tel: +86 21 5339 5999 Fax: +86 21 5426 2030 E-mail: [textile.shanghai@intertek.com](mailto:textile.shanghai@intertek.com) Website: [Intertek.com](http://Intertek.com)

Attention is drawn to the terms and conditions printed overleaf

TEST REPORT

Number : SHAT06731207  
报告号:



Prepared And Checked By:  
For Intertek Testing Services Ltd., Shanghai

A handwritten signature in black ink, appearing to read "Jennifer Ren".

Jennifer Ren  
General Manager

**Intertek Testing Services Ltd., Shanghai**

2/F, Building No.4, Shanghai Comalong Technology Service Park,  
889 Yishan Road, Shanghai 200233, China  
上海天祥质量技术服务有限公司

中国上海宜山路 889 号上海齐来科技服务园区 4 号楼 2 楼 邮编:200233  
Tel: +86 21 5339 5999 Fax: +86 21 5426 2030 E-mail: textile.shanghai@intertek.com Website: Intertek.com  
Attention is drawn to the terms and conditions printed overleaf



TEST REPORT

Number : SHAT06731207  
报告号:

**Tests Conducted (As Requested By The Applicant)**

测试内容 (以下测试依据申请人要求进行)

- 1 Water Resistance As Received-Hydrostatic Pressure Test Method (ANSI/AAMI PB 70:2012, Section 4.2.1 /AATCC 127-2018, Option 2, Hydrostatic Head Tester, Pressure Gradient At 60 mbar/min Water Pressure):  
防水性能-静水压法 (初始状态样品) (ANSI/AAMI PB 70:2012, Section 4.2.1 /AATCC 127-2018, Option 2, Hydrostatic Head Tester, 水压速率 60 毫巴/分钟):

	<u>Result</u> 结果				<u>Requirement</u> 要求
	Area A1 (Critical Zone Chest To Waist- Front) 区域 A1 (关键区域- 前片-胸部 到腰部)	Area A2 (Critical Zone-Waist To Knee- Front) 区域 A2 (关键区域- 前片-腰部 到膝盖)	Area B (Critical Zone- Sleeve) 区域 B (关 键区域-袖 子)	Area C (Front) 区域 C (前 片)	Level 3 ≥50 cmH <sub>2</sub> O 等级 3 ≥50 厘米
Specimen 1 样本 1	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	
Specimen 2 样本 2	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	
Specimen 3 样本 3	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	
Specimen 4 样本 4	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	
Specimen 5 样本 5	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	>50.0 cm >50.0 厘米	

TEST REPORT

Number : SHAT06731207  
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

Water Resistance As Received-Hydrostatic Pressure Test Method (CONT'D)

防水性能-静水压法(续)

	<u>Result</u> 结果	<u>Requirement</u> 要求
	<u>Area D (Back)</u> 区域 D (后片)	<u>Level 3 <math>\geq 50</math> cmH<sub>2</sub>O</u> 等级 3 $\geq 50$ 厘米
Specimen 1 样本 1	>50.0 cm >50.0 厘米	
Specimen 2 样本 2	>50.0 cm >50.0 厘米	
Specimen 3 样本 3	>50.0 cm >50.0 厘米	
Specimen 4 样本 4	>50.0 cm >50.0 厘米	
Specimen 5 样本 5	>50.0 cm >50.0 厘米	

Remark:

The Barrier Performance Of All Critical Zone Components, Including Seams And Points Of Attachments, Shall Be Determined. The Classification Of Surgical Gown Shall Be A Number Denoting The Performance Of The Critical Zone Component Having The Lowest Barrier Performance.

备注:

所有关键区域的阻隔性能都应被考虑, 包括缝和附件, 隔离服的等级基于关键区域中最低的阻隔性能判定。

TEST REPORT

Number : SHAT06731207  
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

2 Water Resistance As Received - Impact Penetration Test Method (ANSI/AAMI PB 70:2012, Section 4.2.1 /AATCC 42-2017):

防水性能 -冲击渗透法 (初始状态样品) (ANSI/AAMI PB 70:2012, Section 4.2.1 /AATCC 42-2017) :

	<u>Result</u> 结果				<u>Requirement</u> 要求
	Area A1 (Critical Zone Chest To Waist- Front) 区域 A1 (关键区域- 前片-胸部 到腰部)	Area A2 (Critical Zone-Waist To Knee- Front) 区域 A2 (关键区域- 前片-腰部 到膝盖)	Area B (Critical Zone- Sleeve) 区域 B (关键区 域-袖子)	Area C (Front) 区域 C (前片)	Level 3 ≤1.0g 等级 3 ≤1.0 克
(Grams Of Water Absorbed) (吸水量, 克)					
Specimen 1 样本 1	Negligible 忽略不计	0.1 g 0.1 克	Negligible 忽略不计	Negligible 忽略不计	
Specimen 2 样本 2	Negligible 忽略不计	0.1 g 0.1 克	0.1 g 0.1 克	Negligible 忽略不计	
Specimen 3 样本 3	0.1 g 0.1 克	Negligible 忽略不计	0.1 g 0.1 克	Negligible 忽略不计	
Specimen 4 样本 4	0.1 g 0.1 克	0.1 g 0.1 克	Negligible 忽略不计	Negligible 忽略不计	
Specimen 5 样本 5	Negligible 忽略不计	Negligible 忽略不计	0.1 g 0.1 克	Negligible 忽略不计	

TEST REPORT

Number : SHAT06731207

报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

Water Resistance As Received - Impact Penetration Test Method (CONT'D)

防水性能 - 冲击渗透法(续)

Area D (Back)

区域 D

(后片)

Level 3  $\leq$  1.0g

等级 3  $\leq$  1.0 克

(Grams Of Water Absorbed)

(吸水量, 克)

Specimen 1

样本 1

Specimen 2

样本 2

Specimen 3

样本 3

Specimen 4

样本 4

Specimen 5

样本 5

Negligible

忽略不计

Negligible

忽略不计

0.1 g

0.1 克

0.1 g

0.1 克

Negligible

忽略不计

Remark:

The Barrier Performance Of All Critical Zone Components, Including Seams And Points Of Attachments, Shall Be Determined. The Classification Of Surgical Gown Shall Be A Number Denoting The Performance Of The Critical Zone Component Having The Lowest Barrier Performance.

备注: 所有关键区域的阻隔性能都应被考虑, 包括缝和附件, 隔离服的等级基于关键区域中最低的阻隔性能判定。

End of Report

Remark: The testing data and result issued by this report is just for reference only, not be used as the evidence to the society in the territory of the People's Republic of China.

备注: 本报告所出具的检测数据及结果仅供参考, 在中华人民共和国境内对社会不具有证明作用。

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.

本报告仅基于申请人的指示及/或申请人提供的信息和材料而作出, 不应视为采取任何行动的建议。关于本报告, Intertek 不对客户以外的任何人负有谨慎责任或其他责任, Intertek 对客户也只在向其申请人提供服务的条件条款有明确规定的范围承担责任。Intertek 不就本报告作出除前述条件条款范围之外的任何明示或隐含形式的担保或陈述。Intertek 致力于在勤勉细致的基础上进行审核, 不对因本报告引起的或与本报告有关的任何损失承担任何责任, 包括合同、侵权、法规或其它责任, 除非诉讼结果显示为因 Intertek 严重疏忽或故意的不当行为而造成。

未经本实验室书面批准, 不得复制本检测报告 (全文复制除外)。